

Very high performance lubricant using ELF Advanced Synthetic Technology, « Fuel Economy », intended for all Gasoline and Diesel car engines.



1 Applications

- | | |
|--|---|
| All Gasoline and Diesel engines, | <ul style="list-style-type: none"> Recommended for all Gasoline engines (multivalve, turbocharged, with or without catalytic converter) and all Diesel engines – with or without turbocharging – in cars and light vans. |
| Direct injection | <ul style="list-style-type: none"> Particularly recommended to meet the enhanced requirements of direct injection Diesel engines. |
| The most severe journeys, all times of year | <ul style="list-style-type: none"> Suitable for all journeys (in town, on highways and motorways) and particularly in severe conditions. |
| “Vigorous” driving | <ul style="list-style-type: none"> For all driving styles, particularly “vigorous” and high speeds. |

Refer to the maintenance book of your vehicle to know the recommendation of the manufacturer

2 Performances

International Specifications	ACEA : A5/B5 API: SL/CF
OEM Approvals	RENAULT RN0700 (except 2.0 16V Renault Sport, 2.0 T Renault Sport, V6 Renault Sport) FORD WSS-M2C913-D (back-compatible FORD WSS-M2C913-C) JAGUAR STJLR 03.5003

3 Customer Benefits

- | | |
|--|--|
| Fuel saving | <ul style="list-style-type: none"> Saves fuel. |
| Very advanced performance | <ul style="list-style-type: none"> Outstanding engine protection particularly against wear. |
| Extension of engine’s lifetime | <ul style="list-style-type: none"> Outstanding thermal stability and oxidation resistance, preventing any degradation even in very severe conditions |
| Extension of oil change intervals | <ul style="list-style-type: none"> ELF Evolution 900 SXR 5W-30 has been engineered in order to comply with car manufacturers' requirements in terms of extended oil change intervals. |

4 Characteristics

	METHOD	UNITS	SAE GRADE 5W-30
Density at 15°C	ASTM D1298	kg/m ³	857
Viscosity at 40°C	ASTM D445	mm ² /s	55,6
Viscosity at 100°C	ASTM 445	mm ² /s	9,9
Viscosity index	ASTM D2270	-	170
Pour point	ASTM D97	°C	-36
Flash point	ASTM D92	°C	230
T.B.N.	ASTM D2896	mgKOH/g	10

The typical characteristics mentioned represent mean values